

CLASSIC No. 40

Article Description	Embroidery Rayon
Composition	100% viscose filament
Harmonised Tariff Number	540120100
Count	135 dtex x 2 / 120 den x 2
Make Up Available	1000 m spool / 5000 m cone

Fastness Rating – Scale 1 (worst) – 5 (best)

Fastness to washing at 95°C	DIN EN ISO 105-C04/M & S C4A	4-5
Fastness to water (damp for 4hrs at 37°C)	DIN EN ISO 105-E01/M & S C6	4-5
Fastness to rubbing dry (10 rubs on dry white Fabric)	DIN EN ISO 105-X12/M & S C8	4
Fastness to rubbing wet (10 rubs on wet white Fabric)	DIN EN ISO 105-X12/M & S C8	3-4
Fastness to dry cleaning	DIN EN ISO 105-D01	4-5
Fastness to saliva and perspiration according to § 35 LMBG		fast

Fastness Rating – Scale 1 (worst) – 8 (best)

Fastness to light (100hrs xenon light)	DIN EN ISO 105-B02	6-7
Due to different dye stuffs not applicable to all colors.		

Mechanical – Technological Values

Tensile Strength cN (force until thread breaks, in Centinewton)	DIN EN ISO 2062	ca. 680
Elongation (% of stretch extension with weight tension until breaks)	DIN EN ISO 2062	ca. 18
Shrinkage (shrinkage at boiling water)	DIN 53866 T2	1-2 %

Recommendations for care



Color Card No. 429

Oeko-Tex



To improve this product Madeira reserves the right to alter the specifications or modify the appearance of products without notice. Information and technical data in this document are guidelines and no warranted characteristics. Small variations due to production process are possible.

dtex = decitex = weight in grams of 10,000m of yarn; den = denier = weight in grams of 9,000m of yarn
 1 denier = 1,111 decitex; dtex x 2 = two-ply of yarn; den x 2 = two-ply of yarn
 cN = Centinewton: 1 Centinewton ≈ 1,02 gram;

