

LUNA

Article Description	Light-Storing & Emitting Embroidery Thread
Composition	100% Polyester
Harmonised Tariff Number	540110140
Count	dtex 145 x 2 / den 130 x 2
Make Up Available	500 m Spool

Mechanical-Technological Values

Tensile Strength cN (force until thread breaks, in Centinewton)	DIN EN ISO 2062	approx. 640
Elongation (% of stretch extension with weight tension until breaks)	DIN EN ISO 2062	approx. 35

Recommendations for care



Oeko-Tex



To improve this product Madeira reserves the right to alter the specifications or modify the appearance of products without notice. Information and technical data in this document are guidelines and no warranted characteristics. Small variations due to production process are possible.

dtex = decitex = weight in grams of 10,000m of yarn; den = denier = weight in grams of 9,000m of yarn
 1 denier = 1,111 decitex; 1 cN/Centinewton = slightly more than 1 gram
 dtex x 2 = two-ply of yarn; den x 2 = two-ply of yarn